

TEST REPORT

No.: TJIN1906009205ML

Date: Jun 24, 2019

Page: 1 of 3



CUSTOMER NAME: YUANXIAN HIGH-TECH MATERIAL TRADING (TIANJIN) CO., LTD

ADDRESS: 1116, HUA YING BUILDING, CENTER AVENUE, TIANJIN AIRPORT

ECONOMIC ZONE, TIANJIN PILOT FREE TRADE ZONE, TIANJIN,

CHINA

Sample Name : Pre-stressed Concrete Steel Strand

Product Specification : EN10138-3-Y1860S7-15.2-F2-C1

Material and Mark : SWRH82B

Other Information : Coil No.C19062030-2

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

Date of Receipt : Jun 17, 2019

Testing Start Date : Jun 17, 2019

Testing End Date : Jun 24, 2019

Test result(s) : For further details, please refer to the following page(s)

(Unless otherwise stated the results shown in this test report refer only to

the sample(s) tested)

Signed for

SGS-CSTC Standards Technical

Services(Tianjin) Co., Ltd

Kevin Zhou

Authorized signatory





TEST REPORT

No.: TJIN1906009205ML

Date: Jun 24, 2019

Page: 2 of 3

1. Test item: Tensile test

Test method: prEN 10138-3:2009(E)

Test item	Specimen type	Tensile strength (R _m) (MPa)	Maximum force (F _m) (kN)	Proof force (F _{p0.1}) (kN)	elasticity modulus (E) (GPa)	Elongation after fracture(A) L _o =600mm (%)	Conclusion
Req.		≥1860	259~298	≥228	195	≥3.5	
1	Unmachined specimen	1928	268	248	195	5.0	Pass

Note: The results comply with the requirement of prEN 10138-3:2009(E)Steel name Y1860S7-d15.2. The above test was carried out by an external laboratory assessed as competent.

2. Test item: Dimension Measurement

Test standard: EN10138-3-2009

No.	Test Item	Nominal value	EN10138-3-2009 requirements	Measure Result	Conclusion
1	Diameter(mm)	15.2		15.28	
2	Cross-sectional area(mm²)	139		140.8	
3	Mass per meter (g/m)	1086	±2%	1100.3	Pass



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <a href="http://www.sgs.com/en/Terms-and-Conditions.gsg.acm.en/Terms-and-Condi



TEST REPORT

No.: TJIN1906009205ML

Date: Jun 24, 2019

Page: 3 of 3



****** End of report*****



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <a href="http://www.sgs.com/en/Terms-and-Conditions for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document aspx.
Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullee stent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Building C-11, No.80, Haiyun Street, TEDA, Tianjin, China 300457 中国・天津・经济技术开发区海云街80号C-11厂房 邮编: 300457

t (86-22) 5999 5008 f (86-22) 5999 5016 t (86-22) 5999 5008 f (86-22) 5999 5016

www.sgsgroup.com.cn e sgs.china@sgs.com